

Stärke	EPS 30	XPS blau	XPS lila	XPS Plus lila		Klebit PET Eco50	PIR 33	SwissporPIR Premium	Kerdyn 115	PUR 500
	W/mk 0.033	W/mk 0.035-0.039	W/mk 0.034	W/mk 0.025-0.027		W/mk 0.032	W/mk 0.025-0.027	W/mk 0.02	W/mk 0.0332	W/mk 0.087
10 mm	2.11	2.16	2.19				1.80			3.46
15 mm	1.60						1.34			2.87
20 mm	1.29	1.32	1.35	1.03*	1.10	1.25	1.07	0.89	1.30	2.45
25 mm	1.08						0.88			2.14
30 mm	0.93	0.95	0.97	0.73*	0.78	0.90	0.76	0.63	0.93	1.90
35 mm	0.81									1.71
40 mm	0.72	0.74		0.57*	0.61	0.70	0.59	0.48	0.73	1.55
45 mm										1.42
50 mm	0.59	0.61		0.46*	0.50	0.58	0.48	0.39	0.60	1.31
55 mm										1.21
60 mm	0.50	0.52		0.39*	0.42	0.49	0.40	0.33	0.51	1.13
70 mm	0.44					0.42			0.44	1.00
80 mm	0.39	0.40		0.30*	0.32	0.37	0.31	0.25	0.39	0.89
90 mm						0.34			0.35	
100 mm	0.31	0.32				0.30	0.25	0.20	0.31	
120 mm	0.26	0.27				0.26		0.17	0.26	
140 mm	0.23	0.23		* bei beidseitiger gasdichter Kaschierung (Sandwich)		0.22		0.15	0.23	
160 mm	0.20	0.21				0.19		0.13	0.20	
180 mm	0.18	0.18				0.17		0.11		
200 mm	0.16	0.17				0.16		0.10		